



## Specification

**CPP-film**

**8110/20**

property	test method	unit	value
thickness	DIN 53370	μm	30 -75
width		mm	max. 1640
density	DIN 53479	g/cm <sup>3</sup>	0,905
weight per area	DIN 53352	g/m <sup>2</sup>	27 - 68
tensile strength at break -longitudial direction -transverse direction	DIN 53455-6-5	N/mm <sup>2</sup> N/mm <sup>2</sup>	for 30 μm > 40 > 27
percentage elongation at break - longitudinal direction - transverse direction	DIN 53455-6-5	% %	for 30 μm > 490 > 490
opacity	DIN 53146	%	0 – 1
gloss 60° -inside -outside	DIN 67530		> 100 > 100